



Super H-2[®] Catalyst Specification

| <i>Chemical Analysis</i> (110 °C dry weight basis) | | |
|--|------------|------------|
| Palladium (Nominal wt%) | | 0.2 |
| Silicon Carbide | | Balance |
| <i>Chemical Properties</i> (110 °C dry weight basis) | | |
| | <u>Min</u> | <u>Max</u> |
| Bulk Density, g/cc (packed) | 0.9 | 1.3 |
| Crush Strength, kg | 9 | |
| Size (Nominal, mm) | 3 | 5 |

Per the Non-disclosure Agreement on this Patented Proprietary Catalyst, executed between OxyVinyls, LP and your company, the information provided here is strictly confidential and is not to be disclosed to any third party, without the permission of OxyVinyls, LP.