

CALCIUM CHLORIDE 83-87% FLAKE

General Description <u>Appearance:</u> White, odorless flakes	Features: Meets ASTM D98 and AASHTO M144 requirements
---	---

Property	Specification Range
Calcium Chloride (wt. %)	83 Min.
Total Alkali Chlorides as NaCl (wt. %)	6.0 Max.
Total Magnesium as MgCl ₂ (wt. %)	0.5 Max.
Calcium Hydroxide (wt. %)	0.2 Max.
Bulk Density, Tapped (lb/ft ³)	51 – 61
<u>Particle Size Distribution</u>	
Passing 3/8 in. (9.5 mm) sieve (wt. %)	100 Min.
Passing No. 4 (4.76 mm) sieve (wt. %)	80 Min.
Passing No. 30 (0.6 mm) sieve (wt. %)	5 Max.

Total Alkali Chlorides as NaCl (wt. %), Total Magnesium as MgCl₂ (wt. %) and Calcium Hydroxide (wt. %) limits are shown on an “Active Ingredient” basis.

Important: The information presented herein, while not guaranteed, was prepared by technical personnel and is true and accurate to the best of our knowledge. NO WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE, OR WARRANTY OR GUARANTY OF ANY OTHER KIND, EXPRESS OR IMPLIED, IS MADE REGARDING PERFORMANCE, SAFETY, SUITABILITY, STABILITY OR OTHERWISE. This information is not intended to be all-inclusive as to the manner and conditions of use, handling, storage, disposal and other factors that may involve other or additional legal, environmental, safety or performance considerations, and OxyChem assumes no liability whatsoever for the use of or reliance upon this information. While our technical personnel will be happy to respond to questions, safe handling and use of the product remains the responsibility of the customer. No suggestions for use are intended as, and nothing herein shall be construed as, a recommendation to infringe any existing patents or to violate any Federal, State, Local or Foreign laws.